

ARCOR®

Chemical

Resistance

Guidelines

ALKALIES

SOLVENTS

	Aluminum Chloride 50%	Ammonia 20%+	Ammonium Chloride 50%	Ammonium Hydroxide 40%	Ammonium Nitrate-Sat	Ammonium Persulfate	Ammonium Sulfate-Sat	Calcium Chloride 50%	Calcium Hydroxide-Sat	Calcium Hypochlorite 15%	Copper Fluoroborate	Ferric Chloride;Ferrous Sulfate	Sodium Benzoate	Sodium Carbonate(Soda Ash)	Sodium Bicarbonate-Sat	Sodium Bisulfate;Sodium Chloride-Sat	Sodium Glutamate	Sodium Hydroxide to 50%	Sodium Hypochlorite to 10%	Sodium Propionate	Sodium Sulfate/Sulfite-Sat	Trisodium Phosphate-Sat	Zinc Nitrate	Methanol	Ethanol	Butanol; Propanol	Benzene;Xylene;Toluene	Trichloroethane; Cellosolve	Formaldehyde to 37%	Gasoline; Fuel Oil; Crude Oil	Acetone;MEK;Methylene Chloride	
Multi 3.6	EE-101	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1
	EE-111	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1
	EE-121	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1
	EE-951	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1
VICOR® FLOORINGS	EE-70	1	1	1	1	1	1	1	1	3	1	3	1	1	1	1	1	1	3	1	1	1	3	*	3	3	3	3	3	3	2	3
	EE-71	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	3	2	1	1	1	1	1	1	3
	EE-72	1	1	1	1	1	1	1	1	3	1	3	1	1	1	1	1	1	2	1	1	1	2	*	3	3	3	3	3	3	2	3
	EE-75	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	3	2	1	1	1	1	1	1	3
	EE-78	1	1	1	1	1	1	1	1	3	1	3	1	1	1	1	1	1	3	1	1	1	3	*	3	3	3	3	3	3	2	3
	EE-79	1	1	1	1	1	1	1	1	3	1	3	1	1	1	1	1	1	3	1	1	1	3	*	3	3	3	3	3	3	2	3
	EE-91	1	1	1	1	1	1	1	1	3	1	3	1	1	1	1	1	1	3	1	1	1	3	*	3	3	3	3	3	3	2	3
	EE-92	1	1	1	1	1	1	1	1	1	2	1	1	1	1	1	1	1	2	1	1	1	2	3	2	1	1	1	1	1	1	3
	EE-95	1	1	1	1	1	1	1	1	1	2	1	1	1	1	1	1	1	2	1	1	1	2	3	2	1	1	1	1	1	1	3
	EE-96	1	1	1	1	1	1	1	1	1	2	1	1	1	1	1	1	1	2	1	1	1	2	3	2	1	1	1	1	1	1	3
	EE-97	1	1	1	1	1	1	1	1	1	2	1	1	1	1	1	1	1	2	1	1	1	2	3	2	1	1	1	1	1	1	3
	EE-99	1	1	1	1	1	1	1	1	3	1	3	1	1	1	1	1	1	3	1	1	1	3	*	3	3	3	3	3	3	1	3
ARCOR® COATINGS	S-16	1	1	1	1	1	1	1	1	3	1	3	1	1	1	1	1	1	3	1	1	1	3	3	2	1	1	1	1	1	1	3
	S-20	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	3	2	1	1	1	1	1	1	3
	S-30	1	1	1	1	1	1	1	1	2	1	2	1	1	1	1	1	1	2	1	1	1	2	*	2	2	2	2	2	2	1	3
	S-30 PRIME	1	1	1	1	1	1	1	1	2	1	2	1	1	1	1	1	1	2	1	1	1	2	*	2	2	2	2	2	2	1	3
	ARCHANE	1	1	1	1	1	1	1	1	3	1	3	1	1	1	1	1	1	3	1	1	1	3	*	3	3	3	3	3	3	3	3
	SPRAYTHANE	1	1	1	1	1	1	1	1	3	1	3	1	1	1	1	1	1	3	1	1	1	3	*	3	3	3	3	3	3	3	3
	TS-RB	1	1	1	1	1	1	1	1	3	1	3	1	1	1	1	1	1	3	1	1	1	3	*	3	3	3	3	3	3	2	3
	ARCRETE	1	1	1	1	1	1	1	1	3	1	3	1	1	1	1	1	1	3	1	1	1	3	*	3	3	3	3	3	3	2	3
VICOR® COATINGS	EE-10	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	3	2	1	1	1	1	1	1	3
	EE-11	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	3	2	1	1	1	1	1	1	3
	EE-11 Prime	1	1	1	1	1	1	1	1	2	1	2	1	1	1	1	1	1	2	1	1	1	2	*	2	2	2	2	2	2	1	3
	EE-15	1	1	1	1	1	1	1	1	2	1	2	1	1	1	1	1	1	2	1	1	1	2	*	2	2	2	2	2	2	1	3
	EE-31.1	1	1	1	1	1	1	1	1	2	1	2	1	1	1	1	1	1	2	1	1	1	2	*	2	2	2	2	2	2	1	3
	EE-80	1	1	1	1	1	1	1	1	4	1	4	1	1	1	1	1	1	4	1	1	1	4	*	4	3	3	3	3	3	2	3

KEY

1:Excellent: Suitable for Immersion

2:Very Good: Suitable for Immersion

3:Good: Suitable For Secondary Containment's

4:Fair: Spill / Splash

*:Not Recommended