

Resistance of Ultra-S Natural in a variety of harsh chemical media
 12 month results.

FLUID\PRODUCT	#	ULTRA S Hardness	ULTRA S Weight	ULTRA S Comment
98% Sulfuric	1	85/83	8.84/8.76	
	2	85/83	8.87/8.79	
<i>% Change</i>		-2.5	-1	NO CHANGE
37% HCl	1	85/83	8.92/8.99	
	2	85/83	8.51/8.64	
<i>% Change</i>		-2.5	0.8	NO CHANGE
85% Phosphoric	1	85/85	8.59/8.6	
	2	85/85	8.55/8.58	
<i>% Change</i>		0	0.4	NO CHANGE
50% H2O2	1	85/35	8.73/9.48	
	2	85/35	8.52/9.27	
<i>% Change</i>		-59	8.7	RED-BLISTERED
50% NaOH	1	85/85	8.94/8.95	
	2	85/85	8.67/8.66	
<i>% Change</i>		0	0	NO CHANGE
50% KOH	1	85/85	8.98/8.97	
	2	85/85	8.68/8.67	
<i>% Change</i>		0	0	NO CHANGE
AIR (CONTROL)	x	0	0	RED