

Product Technical Data Sheet

ARCOR™ 2213

REVISED 9/2020.1

GENERIC TYPE: AMINE CURED 100% SOLIDS EPOXY RAPID CURE REBUILDING COMPOUND

DESCRIPTION AND RECOMMENDED USES: ARCOR® 2213 Stick is a solvent free, two-component epoxy paste provided in an easy to use stick form which contains both the Activator and Base components. Simply cut or twist off a desired amount and knead with your gloved fingers. Rapid cure makes 2213 ideal for emergency repairs. It is corrosion resistant, steel reinforced for excellent wear. It can be sanded, drilled, tapped, filed, machined. Can be painted with epoxy, urethane or acrylics. ARCOR® 2213 sets in 5 minutes and can be put into full service within 1 hour.



Certified to Standard 61 by The National Sanitation Foundation for use in contact with drinking water.

FOR INDUSTRIAL USE ONLY

SPECIFICATION DATA

TEMPERATURE:

Max.250°F(121°C); Spike to 300°F(149C)
Recommended force cure at 250°F@ 2 hrs.
Dry to 400°F (190C); Spike to 500°F
(246C)(3 hrs)

Temperature resistance will vary depending on chemical exposure. Consult ARCOR.

CHEMICAL RESISTANCE:

Water:	Excellent
Alkalis:	Excellent
Dilute Acids:	Good
Hydrocarbons:	Excellent
Alcohols, Ketones:	Excellent

ABRASION: Excellent

FLEXIBILITY: Fair. Excellent with Polyester or Fiberglass Cloth

APPLICATIONS:

- Fill Cracks & Voids
- Rebuild Rust/Corrosion Damage
- Repair Stripped Threads
- Repair Leaking Pipe & Duct
- Anchor Equipment
- Rebuild Small Parts

SOLIDS BY VOLUME: 100%

VISCOSITY: 150,000+ cps

POT LIFE: 5 MIN/100gr @ 72°F(22.2°C)

MIX RATIO: 1:1 by Volume (Base: Activator)

COLOR: Gray (when mixed)

SHELF LIFE: 5 Years at 55-95°F (13-35°C)

COVERAGE: 1604/#mils = ft²/gal/coat;
149/#mils = M²/Gal; 3,785/#microns = M²/Gal
1mil = 25 micron; 1 Gal = 3.785 L; 10.77ft² = M²

WEIGHT PER GALLON: 18.5 lbs. (8.4 KG)
4.9 lbs. (2.2 KG)/Liter

FILM THICKNESS:

Final DFT Specified by Need; fill voids as needed

ORDER INFORMATION: To place orders and/or obtain pricing information contact:

Novolac Epoxy
Technologies Inc.
PO Box 990
Harwich, MA 02645
Tel: 508-385-5598;
Email:Sales@NovolacEpoxy.com

Manufacturer, Novolac Epoxy Technologies Inc., makes no warranty either expressed or implied including warranties of merchantability or fitness for a particular purpose for this product. Under no circumstances will the manufacturer be liable for incidental, consequential or other damages, breach of warranty, strict liability, or any other theory arising out of use of this product. The information and or recommendations contained herein are based on standard Product and are proprietary and furnished solely for the use of our customers. This information is provided in good faith and believed to be true and accurate as of the date/version of this document. As the manufacturer has no control over the use conditions or application process of the parties using this product, the manufacturer cannot accept responsibility for loss, injury or other damages resulting from the use of the Product or this or any other information provided by the manufacturer. Therefore, no guarantees of any kind, expressed or implied, are made by the manufacturer, Novolac Epoxy Technologies Inc., regarding this, or any, product manufactured by them or any contracted or licensed manufacturer. ARCOR® epoxy products do not provide structural integrity or improvement. They are only used to provide protection from corrosion, wear, abrasion and chemical attack on a given substrate and only to the extent provided for in the Data Sheets, Technical Data Sheets, Safety Data Sheets and any other information as supplied in writing directly from manufacturers technical support.

Application Sheet

ARCOR™ 2213

REVISED 3/2019.1

SEE MATERIAL SAFETY DATA SHEET (SDS) BEFORE HANDLING THIS PRODUCT;

download @ www.ArcorEpoxy.com; ChemTel ERS / MOD Tel US: 800-255-3924; Outside US: +001-813-248-0585

SURFACE PREPARATION:

Steel surfaces are to be abrasive blasted with chloride free abrasive. Exterior applications to SSPC SP-10 Near White metal finish. Immersion applications to SSPC SP-5 White metal 4+ mil profile. Grind flat all burrs, weld seams, radius sharp edges. Fresh blasted ferrous surfaces to be primed with S-20 immediately to prevent oxidation of surface.

Concrete surfaces should be degreased if oil and grease contamination is present. Degreased surface shall be high pressure washed, acid etched, and high pressure washed again so surface is clean and free of all grease, oils and surface laitance. Existing coatings should be abrasive blasted to clean concrete. Prime with EE-10.

MIXING:

Thoroughly mix Activator into Base with mixing stick or drill with low speed mixing blade scraping sides and bottom of container or mixing board. Mix by Volume 2-parts Base to 1-part Activator. Or by weight 100 grams Base to 50 grams Activator. Mix thoroughly to produce an even colored and streak-free material.

THINNING: Never thin.

APPLICATION:

Brush: medium to stiff bristle of sufficient quality that bristles do not pull out and stick in coating. Trim or tape to <1" nap.

Roller: good quality 1/8" nap.

ARCOR Cartridge Sprayer: Heat to 140F(60C). Piston '3'; Tip Air '3'.

Plural Spray: .029-.035 RAC tip, 3,000-4,500 PSI, Heat to 160°F Base, 120°F Activator. Ambient Temperature and Humidity will affect temperature and pressure setting. Consult ARCOR.

Airless Spray: 029-.035 RAC tip, 4,500-5,500 PSI(60:1+). Recommended in-line heater at 120° to 135°F (Caution: Short Pot-Life).

Ambient Temperature and Humidity will affect temperature and pressure setting. Contact ARCOR.

All spray equipment should employ traps to prevent water and oil from contaminating coating and screens to prevent particulate contamination.

APPLICATION TEMPERATURE:

Material: Keep between 55 to 95°F(17 to 35°C). Substrate: Keep between 45 to 105°F(7 to 40°C). The difference in temperature of the substrate and the material should never exceed 10°F(5°C). Substrate shall be a minimum of 5°F(3°C) above dew point. Do not apply if relative humidity exceeds 90%. If necessary heat metal prior to surface preparation using electric heater or heat lamp. Never use gas, oil or kerosene heaters as they will leave a greasy residue on metal surface. For best results keep all material in warm area overnight(75°F+, 24°C) for ease of mixing. If necessary base component of material can be heated by microwave for 30-45 seconds for a 1 KG Base unit.. If necessary let material cool before application to allow for more pot life during application.

OVERCOAT / CURE TIME:

By brush, roller or squeegee recoat while material is still soft, but tack-free, between 3-12 hours at 77°F(25°C). **IMPORTANT:** If overcoat window is exceeded abrade surface with course sandpaper, grinder or brush blast and wipe with MEK or Acetone. By spray application recoat between 2-12 hours at 77°F(25°C). Full cure before immersion recommended 72 hours at 77°F(25°C). Add 1 hour's additional cure time for each 10°F(-12.2°C) below 77°F(25°C). For highly aggressive environments Force Cure with heat for best performance for 8 hours at 150°F (66°C), 2 hours at 250°F (121°C).

CLEAN UP: Clean tools immediately with M.E.K., Acetone or similar. Isopropyl Alcohol(98+%) can be used in solvent restricted areas

WARNING: Base contains epoxy resin. Activator contains alkaline amines, a strong sensitizer. May cause skin irritation, sensitization or other allergic responses. Use with good ventilation, particularly if heated or sprayed. Prevent all contact with skin or eyes. Wear protective clothing, goggles, gloves or barrier creams. Keep containers closed when not in use. Wash thoroughly after handling. In case of skin contact immediately wash with soap and water. In case of eye contact, flush with water for 15 minutes. If irritation persists seek medical attention. Consult the Product Safety Data Sheets (SDS) BEFORE USE!

Manufacturer makes no warranty either expressed or implied including warranties of merchantability or fitness for a particular purpose for this product. Under no circumstances will the manufacturer be liable for incidental, consequential or other damages, breach of warranty, strict liability, or any other theory arising out of use of this product. ARCOR® epoxy products do not provide structural integrity or improvement. They are only used to provide protection from corrosion, wear, abrasion and chemical attack on a given substrate and only to the extent provided for in the Data Sheets, Technical Data Sheets, Safety Data Sheets and any other information as supplied in writing directly from manufacturers technical support.

The information and or recommendations contained herein are based on standard Product and are proprietary and furnished solely for the use of our customers. This information is provided in good faith and believed to be true and accurate as of the date/version of this document. As the manufacturer has no control over the use conditions or application process of the parties using this product, the manufacturer cannot accept responsibility for loss, injury or other damages resulting from the use of the Product or this or any other information provided by the manufacturer. Therefore, no guarantees of any kind, expressed or implied, are made by the manufacturer, Novolac Epoxy Technologies Inc., regarding this, or any, product manufactured by them or any contracted or licensed manufacturer.