ARCOR
EPOXY TECHNOLOGIES

ProductDataSheet

ARCOR™ EE-72

REVISED 5/2024

GENERIC TYPE: AMINE CURED 100% SOLIDS EPOXY TOPCOAT

DESCRIPTION AND RECOMMENDED USES: ARCOR™ EE-72 is a solvent free, high functionality epoxy Novolac coating suitable as a self-leveling flooring, particularly in aggressive environments with exposure to acids and alkalis. **ARCOR™ EE-72** produces a tough, chemical resistant coating on concrete, ferrous and non-ferrous metals. Use of Reactive Flexibilizing agents gives excellent flexibility without sacrificing chemical resistance making **EE-72** ideal for concrete or metal floors with thermal, design or structural stress, without the need for fiberglass mat reinforcement. High abrasion resistance in an easy to clean surface. **ARCOR™ EE-72** is suitable for hand or spray application at up to 100 mils per coat.

FOR INDUSTRIAL USE ONLY

SPECIFICATION DATA

TEMPERATURE: Immersion service Max.245ºF (118ºC); Dry to 400ºF (3 Hrs).

CHEMICAL RESISTANCE:

Water:	Excellent
Alkalies:	Excellent
Inorganic Acids:	Excellent
Organic Acids:	Excellent
Organic Solvents:	Excellent

ABRASION: Very Good

FILM THICKNESS: 20 -100 mils(.51-2.55 mm)/coat Splash: 1 coat, Immersion: 2 coats

FLEXIBILITY: Very Good

Excellent with Cloth Mat; 1.5 oz/ft^2 (.5 KG/M^2)

APPLICATIONS: Aggressive Chemical Secondary Containment Areas, Aggressive Industrial Floors, High Wear Flooring.

SOLIDS BY VOLUME: 100% **VISCOSITY:**2,000-3,000 cps **POT LIFE:** 35 MIN/KG @ 72ºF
MIX RATIO: 2:1 by Volume (Base:Activator) 100 gm: 34 gm by weight

COLOR: Gray (special order colors available)

SHELF LIFE: 5 Years at 55-95ºF (13-35ºC)
COVERAGE: 80 ft^2(7.5 M^2)/ gal @ 20mils
WEIGHT PER GALLON: 10.8 lbs (4.89 KG)
ORDER INFORMATION: To place orders and/or obtain pricing information contact:

Novolac Epoxy Technologies Inc.
28 Jonathan Bourne Drive
Pocasset, MA 02550
TEL: 508-385-5598
Sales@NovolacEpoxy.com

Manufacturer, Novolac Epoxy Technologies Inc., makes no warranty either expressed or implied including warranties of merchantability or fitness for a particular purpose for this product. Under no circumstances will the manufacturer be liable for incidental, consequential or other damages, breach of warranty, strict liability, or any other theory arising out of use of this product. The information and or recommendations contained herein are based on standard Product and are proprietary and furnished solely for the use of our customers. This information is provided in good faith and believed to be true and accurate as of the date/version of this document. As the manufacturer has no control over the use conditions or application process of the parties using this product, the manufacturer cannot accept responsibility for loss, injury or other damages resulting from the use of the Product or this or any other information provided by the manufacturer. Therefore, no guarantees of any kind, expressed or implied, are made by the manufacturer, Novolac Epoxy Technologies Inc., regarding this, or any, product manufactured by them or any contracted or licensed manufacturer. ARCOR® epoxy products do not provide structural integrity or improvement. They are only used to provide protection from corrosion, wear, abrasion and chemical attack on a given substrate and only to the extent provided for in the Data Sheets, Technical Data Sheets, Safety Data Sheets and any other information as supplied in writing directly from manufacturers technical support.

ARCOR
EPOXY TECHNOLOGIES

Application Sheet

ARCOR™ EE-72

REVISED 5/2024

SEE MATERIAL SAFETY DATA SHEET BEFORE HANDLING THIS PRODUCT

SURFACE PREPARATION:

Steel surfaces are to be abrasive blasted with chloride free abrasive. Exterior applications to SSPC SP-10 Near White metal finish. Immersion applications to SSPC SP-5 White metal 3 to 5 mil profile. Grind flat all burrs, weld seams, radius sharp edges. Fresh blasted ferrous surfaces to be primed immediately with **ARCOR™ S-30 Prime or ARCOR™ EE-72** to prevent oxidation of surface.
Concrete surfaces should be degreased if oil and grease contamination is present. Degreased surface shall be high pressure washed. Loose existing coatings should be chipped & ground to remove then entire floor is to be abrasive blasted to remove all existing coating, mastics and laitenance. Clean & grind all cracks & expansion joints. Thoroughly sweep & vacuum.
Prime entire floor with **ARCOR™ EE-80**, **EE-10, EE-72.**

MIXING:

Thoroughly mix Activator into Base with mixing stick or drill with low-speed mixing blade scraping sides and bottom of container or mixing board. Mix by Volume 2 parts Base to 1 part Activator. Or by weight 100 grams base to 34 grams activator. Mix thoroughly to produce an even colored and streak-free material.

THINNING: Never thin.

APPLICATION:

Squeegee: heavy duty rubber 'notched' squeegee
Roller: good quality 3/4" nap.
ARCOR Cartridge Sprayer: Heat to 115F(48C). Piston '3'; Tip Air '3'.
Plural Spray: .017-.025 tip, 3,000-3,500 PSI, Heat to 110ºF Base, 100ºF Activator.
Airless Spray: .019-.027 tip, 3,000-3,500 PSI(45:1). (Caution: Short Pot-Life)
Conventional Spray: Not Recommended.
All spray equipment should employ traps to prevent water and oil from contaminating coating and screens to prevent contamination.

APPLICATION TEMPERATURE:

Material: Keep between 55 to 95ºF(17 to 35ºC). Substrate: Keep between 45 to 105ºF(7 to 40ºC). The difference in temperature of the substrate and the material should never exceed 10ºF(5ºC). Substrate shall be a minimum of 5ºF(3ºC) above dew point. Do not apply if relative humidity exceeds 90%. If necessary, heat metal prior to surface preparation using electric heater or heat lamp. Never use gas, oil or kerosene heaters as they will leave a greasy residue on metal surface. For best results keep all material in warm area overnight (75ºF+, 24ºC) for ease of mixing. If necessary base component of material can be heated by microwave for 30-45 seconds for a 1 KG Base unit or by warm water bath. Heat activator by warm water bath only. If necessary let material cool before application.

OVERCOAT/CURE TIME: By brush, roller or squeegee recoat while material is still soft, but tack-free, between 6-14 hours at 77ºF(25ºC). If overcoat window is exceeded abrade surface with course sandpaper, grinder or brush blast. By spray application recoat between 2-14 hours at 77ºF. Full cure before immersion 72 hours at 77ºF. Add 30 hours additional cure time for each 10ºF below 77ºF. Subtract 12 hours of cure time for each 10ºF above 77ºF. Force Cure with heat for best performance for 4 hours at 200ºF(93ºC), 12 hours at 150ºF(66ºC).

Clean tools immediately after use with M.E.K., Acetone or similar. 98% Isopropyl Alcohol can be used in solvent restricted areas.

WARNING: Base contains epoxy resin. Activator contains alkaline amines, a strong sensitizer. May cause skin irritation, sensitization or other allergic responses. Use with good ventilation, particularly if heated or sprayed. Prevent all contact with skin or eyes. Wear protective clothing, goggles, gloves or barrier creams. Keep containers closed when not in use. Wash thoroughly after handling. In case of skin contact immediately wash with soap and water. In case of eye contact, flush with water for 15 minutes. If irritation persists, seek medical attention. Consult the Product Safety Data Sheets (SDS) BEFORE USE!.
Manufacturer makes no warranty either expressed or implied including warranties of merchantability or fitness for a particular purpose for this product. Under no circumstances will the manufacturer be liable for incidental, consequential or other damages, breach of warranty, strict liability, or any other theory arising out of use of this product. ARCOR® epoxy products do not provide structural integrity or improvement. They are only used to provide protection from corrosion, wear, abrasion and chemical attack on a given substrate and only to the extent provided for in the Data Sheets, Technical Data Sheets, Safety Data Sheets and any other information as supplied in writing directly from manufacturers technical support.
The information and recommendations contained herein are based on standard Product and are proprietary and furnished solely for the use of our customers. This information is provided in good faith and believed to be true and accurate as of the date/version of this document. As the manufacturer has no control over the use conditions or application process of the parties using this product, the manufacturer cannot accept responsibility for loss, injury or other damages resulting from the use of the Product or this or any other information provided by the manufacturer. Therefore, no guarantees of any kind, expressed or implied, are made by the manufacturer, Novolac Epoxy Technologies Inc., regarding this, or any, product manufactured by them or any contracted or licensed manufacturer.

28 Jonathan Bourne Dr., Pocasset, MA 02559 508-385-5798 Tech@ArcorEpoxy.com
www.ArcorEpoxy.com