

# Guidelines For Selecting ARCOR® Coatings

**P** = PRIMARY CONTAINMENT  
**S** = SECONDARY CONTAINMENT  
**F** = FLOORING

**CHEMICAL RESISTANCE**  
 1 = Excellent 2 = Very Good 3 = Good 4 = Fair 5 = Poor

**TEMPERATURE MAXIMUMS**

IMMERSION	IMMERSION SPIKE	DRY	DRY SPIKE
-----------	-----------------	-----	-----------

GENERAL USE		FILM THICKNESS (MILS)	WATER	ALKALIES	INORGANIC ACIDS	ORGANIC ACIDS	ORGANIC SOLVENTS	ABRASION	IMMERSION	IMMERSION SPIKE	DRY	DRY SPIKE
Multi 3.6	EE-101	P/S	8	1	1	1	1	1	400° F	550° F	550° F	650° F
	EE-111	P/S	20	1	1	1	1	1	350° F	500° F	500° F	600° F
	EE-121	P/S	20	1	1	1	1	1	375° F	525° F	500° F	600° F
	EE-121 Prime	P/S	20	1	1	1	1	1	375° F	525° F	500° F	600° F
	EE-941	P/S	20	1	1	1	1	1	350° F	500° F	500° F	600° F
	EE-951	P/S	<1000	1	1	1	1	1	400° F	550° F	550° F	650° F
VICOR® FLOORINGS	EE-70	P/S/F	20	1	3	3	4	3	130° F	160° F	200° F	250° F
	EE-71	S/F	20	1	1	1	3	1	265° F	400° F	400° F	450° F
	EE-72	S/F	20	1	3	3	4	3	130° F	160° F	200° F	250° F
	EE-75	S/F	20	1	1	1	3	1	265° F	350° F	350° F	400° F
	EE-79	S/F	20	1	3	3	4	4	130° F	160° F	200° F	250° F
VICOR® REBUILD	EE-91	P/S/F	<1000	1	3	3	4	3	140° F	180° F	200° F	250° F
	EE-92	P/S	<1000	1	2	2	4	3	265° F	450° F	450° F	475° F
	EE-93	P/S	<1000	1	2	2	4	3	265° F	450° F	450° F	475° F
	EE-94	P/S	<1000	1	2	2	4	3	265° F	450° F	450° F	475° F
	EE-95	P/S	<1000	1	1	1	3	1	265° F	450° F	450° F	475° F
	EE-96	P/S	<125	1	1	1	3	1	300° F	475° F	450° F	475° F
	EE-97	P/S	<200	1	2	2	4	3	265° F	450° F	450° F	475° F
	EE-99	P/S	<1000	1	2	2	4	3	200° F	300° F	400° F	450° F
ARCOR® COATINGS	S-15	P/S	15-30	1	3	3	4	3	130° F	160° F	200° F	250° F
	S-16	P/S	15-30	1	3	3	4	3	130° F	160° F	200° F	250° F
	S-20	P/S/F	20	1	1	1	3	1	265° F	400° F	400° F	450° F
	S-30	P/S/F	20-60	1	2	2	4	3	250° F	300° F	350° F	400° F
	S-30 PRIME	P	20	1	2	4	4	3	225° F	300° F	350° F	400° F
	ARCTHANE	P/S/F	<500	1	3	4	4	5	180° F	200° F	200° F	225° F
	SPRAYTHANE	P/S/F	20	1	3	4	4	5	150° F	180° F	200° F	220° F
	TS-RB	P/S/F	<1000	1	3	3	4	3	140° F	180° F	200° F	250° F
	ARCRETE	P/S/F	<500	1	3	3	4	4	130° F	160° F	200° F	250° F
	EE-60	P/S/F	<500	1	3	4	4	5	180° F	200° F	200° F	225° F
VICOR® COATINGS	EE-65	P/S/F	20	1	1	4	4	5	150° F	180° F	200° F	220° F
	EE-10	P/S/F	20	1	2	1	3	1	265° F	350° F	350° F	400° F
	EE-11	P/S/F	20	1	2	2	4	3	265° F	400° F	400° F	450° F
	EE-11 Prime	P	20	1	2	4	4	3	250° F	300° F	350° F	400° F
	EE-15	P	20	1	3	4	4	3	250° F	300° F	350° F	400° F
	EE-80	P/S/F	1.5	1	3	3	4	4	120° F	140° F	250° F	300° F