

ARCOR®

*Chemical  
Resistance  
Guidelines*

**ACIDS**

	Acetic Acid 10%	Acetic acid 30%	Benzoic Acid-Sat @ 3%	Boric Acid-Sat @ 30%	Butyric Acid 10%	Chromic Acid 10%	Citric Acid 50%	Diglycolic Acid	Fatty Acids	Fluoboric Acid	Formic Acid 10%	Hydrochloric Acid 15%	Hydrochloric Acid 37%	Hydrofluoric Acid	Hydrogen Peroxide to 20%	Hydrochlorous Acid 5%	Lactic Acid to 20%	Maleic Acid 30%	Malic Acid 50%	Methanol Chloride	Methylene Chloride	Nitric Acid 10%	Nitric Acid 30%	Oleic Acid; Oxalic Acid-Sat	Perchloric Acid 35%	Phosphoric Acid 35%	Piric Acid-Sat	Succinic Acid-Sat	Sulfuric Acid 25%	Sulfuric Acid 50%	Sulfuric Acid 98%	Tannic Acid / Tartaric Acid-Sat			
<b>Multi 3.6</b>	EE-101	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1		
	EE-111	1	2	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	3	3	1	1	1	1	1	1	1	1	1	1	1	1		
	EE-121	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	2	2	1	1	1	1	1	1	1	1	1	1	1	1		
	EE-121 Prime	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	2	2	1	1	1	1	1	1	1	1	1	1	1	1		
	EE-941	1	2	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	3	3	1	1	1	1	1	1	1	1	1	1	1	1		
	EE-951	1	2	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	2	2	1	1	1	1	1	1	1	1	1	1	1	1		
<b>VICOR®</b>	EE-70	*	*	1	1	4	4	2	3	1	4	4	*	*	*	2	3	3	1	*	*	*	1	4	3	1	3	3	3	3	*	1			
	EE-71	*	*	1	1	1	1	1	1	1	1	1	2	4	*	2	1	1	1	1	*	*	*	2	3	1	1	1	1	1	1	1	2	1	
	EE-72	*	*	1	1	4	4	2	3	1	4	4	*	*	*	2	3	3	1	*	*	*	*	*	1	4	3	1	3	3	3	3	*	1	
	EE-75	2	*	1	1	1	1	1	1	1	1	1	2	4	*	2	1	1	1	1	*	*	*	2	3	1	1	1	1	1	1	1	2	1	
	EE-79	*	*	1	1	3	4	1	1	1	3	4	*	*	*	2	3	3	1	*	*	*	*	*	1	4	3	1	3	3	3	3	*	1	
<b>VICOR® REBUILD</b>	EE-91	*	*	1	1	3	4	1	1	1	3	4	*	*	*	2	3	3	1	*	*	*	*	*	1	1	1	1	1	1	1	1	2	1	
	EE-92	3	*	1	1	1	1	1	1	1	1	1	2	4	*	2	1	1	1	1	*	*	*	2	3	1	1	1	1	1	1	1	1	2	1
	EE-93	3	*	1	1	1	1	1	1	1	1	1	2	4	*	2	1	1	1	1	*	*	*	2	3	1	1	1	1	1	1	1	1	2	1
	EE-94	3	*	1	1	1	1	1	1	1	1	1	2	4	*	2	1	1	1	1	*	*	*	2	3	1	1	1	1	1	1	1	1	2	1
	EE-95	2	*	1	1	1	1	1	1	1	1	1	2	4	*	2	1	1	1	1	*	*	*	2	3	1	1	1	1	1	1	1	1	2	1
	EE-96	2	*	1	1	1	1	1	1	1	1	1	2	4	*	2	1	1	1	1	*	*	*	2	3	1	1	1	1	1	1	1	1	2	1
	EE-97	3	*	1	1	1	1	1	1	1	1	1	2	4	*	2	1	1	1	1	*	*	*	2	3	1	4	3	1	2	2	3	*	1	
	EE-99	3	*	1	1	2	2	1	1	1	3	4	4	*	*	3	2	3	3	1	*	*	*	3	*	1	4	3	1	2	2	3	*	1	
<b>ARCOR® COATINGS</b>	S-15	*	*	1	1	3	4	1	1	1	3	4	*	*	*	2	3	3	1	*	*	*	*	*	1	4	3	1	3	3	3	3	*	1	
	S-16	*	*	1	1	3	4	1	1	1	3	4	*	*	*	2	3	3	1	*	*	*	*	*	1	4	3	1	3	3	3	3	*	1	
	S-20	2	*	1	1	1	1	1	1	1	1	4	2	4	*	2	1	1	1	1	2	*	*	2	3	1	1	1	1	1	1	1	2	1	
	S-30	4	*	*	*	3	3	1	1	1	2	3	4	*	*	3	1	3	2	1	*	*	*	*	*	4	3	1	2	2	3	*	1		
	S-30 PRIME	*	*	1	1	*	*	*	*	*	*	*	*	*	*	*	*	*	*	*	*	*	*	*	1	*	*	*	*	*	*	*	*	*	
	ARCHANE	*	*	1	1	3	3	1	3	1	3	4	*	*	*	2	3	2	1	*	*	*	*	*	1	4	3	1	3	3	*	*	2		
	SPRAYTHANE	*	*	1	1	3	3	1	3	1	4	4	*	*	*	2	3	2	1	*	*	*	*	*	1	4	3	1	3	3	*	*	2		
	TS-RB	*	*	1	1	3	4	1	1	1	3	4	*	*	*	2	3	2	1	*	*	*	*	*	1	4	3	1	3	3	3	*	1		
ARCRETE	*	*	1	1	3	3	1	1	1	3	3	*	*	*	2	3	3	1	*	*	*	3	*	1	4	3	1	3	3	3	*	1			
<b>VICOR® COATINGS</b>	EE-10	2	*	1	1	1	1	1	1	1	1	2	4	*	2	1	1	1	1	2	*	*	2	3	1	1	1	1	1	1	1	1	1		
	EE-11	2	*	1	1	1	1	1	1	1	1	2	4	*	2	1	1	1	1	2	*	*	2	3	1	1	1	1	1	1	1	1	2	1	
	EE-11 Prime	*	*	*	*	*	*	*	*	*	*	*	*	*	*	*	*	*	*	*	*	*	*	*	*	*	*	*	*	*	*	*	*	*	
	EE-15	4	*	1	1	2	3	1	2	1	2	3	4	*	*	3	1	3	2	1	*	*	*	*	*	1	4	3	1	2	2	3	*	1	
	EE-60	*	*	1	1	3	3	1	3	1	3	4	*	*	*	2	3	2	1	*	*	*	*	*	1	4	3	1	3	3	*	*	2		
	EE-65	*	*	1	1	3	3	1	3	1	4	4	*	*	*	2	3	2	1	*	*	*	*	*	1	4	3	1	3	3	*	*	2		
EE-80	*	*	1	1	4	*	2	4	1	4	4	*	*	*	3	4	3	1	*	*	*	*	*	1	4	3	1	3	3	3	*	2			



**1:Excellent:** Suitable for Immersion  
**2:Very Good:** Suitable for Immersion

**3:Good:** Suitable For Secondary Containment's  
**4:Fair:** Spill / Splash

\*:Not Recommended

