

<b>PRODUCT</b>	<b>WVT</b> g/m <sup>2</sup> •Pa•sec	<b>Permeance</b> Perm (in-lb)	<b>Permeability</b> Perm (inch)
<b>Arcor S-16</b>	1.05 E-7	1.84	0.064
<b>Arcor S-30</b>	1.27 E-7	2.22	0.078

Based on 0.035 inch thick specimens tested per ASTM E-96 (B)  
@ 23C and (100% RH/50% RH)